

**PRODUCT INFORMATION**  
**OKULEN<sup>®</sup> 1000 - AST - FN9200**

OKULEN<sup>®</sup> 1000 - AST - black - FN9200 is an ultra high molecular low pressure polyethylene (UHMW-PE) with a molecular weight of 3 - 5.000.000 g/mol.


OKULEN<sup>®</sup> 1000 has material properties that make it extremely versatile; the material is ideally suited for mechanical engineering – OKULEN<sup>®</sup> 1000 parts are used especially in plant construction and handling technology.

The used additives, type and quantity, meets the cleanliness class FDA §178.3297 (USA) the EU-regulations 1935/2004/EC and 10/2011/EC for “Food contact applications”.

The product fulfills the requirements of the ATEX - Directive for values of resistivity. It was tested on representative samples by the TÜV-Nord (Germany).

Properties:

- Conductive / Antistatic reduced
- ATEX - conform
- TÜV approved
- UV - stabilized
- EU1935/2004 & EU10/2011 - conform
- FDA - conform

Colour:

black FN9200 / similar RAL9005

Range of applications:

- Mechanical engineering
- Conveying industry
- Explosion-proof zones

**PRODUCT INFORMATION**  
**OKULEN® 1000 - AST - FN9200**

## Characteristics and standard values

Properties	Method	OKULEN® 1000 - AST - FN9200	
		SI	US
<b>Physical properties</b>			
Molecular-weight	k.a.	3.0 - 5.0 Mio. g/mol.	3.0 - 5.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.940 g/cm <sup>3</sup>	> 58.682 lb/ft <sup>3</sup>
Notched impact strength	DINENISO 21304-2 (04/2021)	100 kJ/m <sup>2</sup>	47.55 ft-lb/in <sup>2</sup>
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	100 - 110	100 - 110
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 18 N/mm <sup>2</sup>	> 2610 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 150 %	> 150 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	700 N/mm <sup>2</sup>	101500 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.15 - 0.20	~ 0.15 - 0.20
Dynamic Friction	ASTM D 1894 (2014)	~ 0.10 - 0.15	~ 0.10 - 0.15
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	61 - 65 D	61 - 65 D
Ball indentation hardness	DINENISO 2039	35 N/mm <sup>2</sup>	5075 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
<b>Thermal properties</b>			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 135 °C	271.4 - 275 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft <sup>2</sup> -°F
Max. operation temperature	Literature	80 °C	176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
<b>Electrical properties</b>			
Volume resistivity	DINEN 62631-3-1 (01/2017)	<= 1.0E4 Ohm*cm	<= 1.0E4 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	<= 1.0E4 Ohm	<= 1.0E4 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	Ja / Yes	Ja / Yes
ESD-D	---	--- Ohm	--- Ohm
<b>Burning properties</b>			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
<b>Physiological properties</b>			
Food compliant		EU/FDA	EU/FDA

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)