

PRODUCT INFORMATION
OKULEN® 1000 Reg.-multi coloured-FN9005

OKULEN® 1000-Reg. (PE-UHMW)

Ultra high molecular weight low pressure polyethylene with regenerated (recycled) materials.

Colour: black multi-coloured FN9005

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein
Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com

PRODUCT INFORMATION

OKULEN® 1000 Reg.-multi coloured-FN9005

Characteristics and standard values

Properties	Method	OKULEN® 1000 Reg.-multi coloured-FN9005	
Physical properties		SI	US
Molecular-weight	k.a.	> 2.0 Mio. g/mol.	> 2.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) (Method A)	> 0.940 g/cm³	> 58.682 lb/ft³
Notched impact strength	DINENISO 21304-2 (04/2021) (3 mm Double-V-Notch)	> 30 kJ/m²	> 14.265 ft-lb/in²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	130 - 250	130 - 250
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2022)	> 20 N/mm²	> 2900 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2022)	> 150 %	> 150 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2022)	> 700 N/mm²	> 101500 psi
	---	---	---
Static Friction	ASTM D 1894 (2024) (vs. Steel: Surface roughness Rz2)	~ 0.16 - 0.22	~ 0.16 - 0.22
Dynamic Friction	ASTM D 1894 (2024) (vs. Steel : Surface roughness Rz2)	~ 0.10 - 0.17	~ 0.10 - 0.17
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	64 - 68 D	64 - 68 D
Ball indentation hardness	DINENISO 2039	38 N/mm²	5510 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 137 °C	271.4 - 278.6 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft²-°F
Max. operation temperature	Literature	80 °C	176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00020 mm/mm °C	~ 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	< 1.0E+14 Ohm*cm	< 1.0E+14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	< 1.0E+13 Ohm	< 1.0E+13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		---	---

The above data are based on the present knowledge and are given without guarantee. Existing laws and conditions are to be respected by the user of our products. The decision about the suitability of a material for a certain application must be made by the user. We reserve the right to alter the indicated data. The indicated values are for a 15 mm thick sheet, unannealed. Black sheets may have antistatic properties.

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com