

**PRODUCT INFORMATION**  
**OKULEN® 2000 - Mol-black - FN9610**

OKULEN® 2000 - Mol-black - FN9610 is an UHMW-PE Polymer (7 - 9 Mio. g/mol) with high abrasion resistance and excellent sliding properties. Because of the low coefficient of friction this material allows even lower transmission power.

Properties:

- extremely wear resistant
- excellent sliding properties
- self-lubricating
- good chemical resistance
- low maintenance
- longer life time over standard UHMW-PE
- EU1935/2004 - conform (Food)
- EU10/2011 - conform (Food)

Colour:

Mol-black FN9610 / similar RAL 9005

Range of applications:

- Conveying industry
- Machine construction

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)

**PRODUCT INFORMATION**  
**OKULEN® 2000 - Mol-black - FN9610**

## Characteristics and standard values

Properties	Method	OKULEN® 2000 - Mol-black - FN9610	
		SI	US
<b>Physical properties</b>			
Molecular-weight	k.a.	7.0 - 9.0 Mio. g/mol.	7.0 - 9.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.94 g/cm <sup>3</sup>	> 58.682 lb/ft <sup>3</sup>
Notched impact strength	DINENISO 21304-2 (04/2021)	> 100 kJ/m <sup>2</sup>	> 47.55 ft-lb/in <sup>2</sup>
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	80	80
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 18 N/mm <sup>2</sup>	> 2610 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 250 %	> 250 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 680 N/mm <sup>2</sup>	> 98600 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.13 - 0.17	~ 0.13 - 0.17
Dynamic Friction	ASTM D 1894 (2014)	~ 0.09 - 0.13	~ 0.09 - 0.13
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	61 - 65 D	61 - 65 D
Ball indentation hardness	DINENISO 2039	~ 35 N/mm <sup>2</sup>	~ 5075 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
<b>Thermal properties</b>			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 136 °C	271.4 - 276.8 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft <sup>2</sup> -°F
Max. operation temperature	Literature	~ 80 °C	~ 176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
<b>Electrical properties</b>			
Volume resistivity	DINEN 62631-3-1 (01/2017)	< 1E14 Ohm*cm	< 1E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	< 1E13 Ohm	< 1E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
<b>Burning properties</b>			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
<b>Physiological properties</b>			
Food compliant		EU	EU

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)