

PRODUCT INFORMATION
OKULEN® 2000 - blue - FN5884

OKULEN® OK 2000 - blue - FN5884 is an UHMW-PE polymer with a low coefficient of friction. It is a lining material that has been perfected to solve material flow problems.

Properties:

- good sliding properties
- improved low coefficient of friction
- good notched impact strength
- very good wear resistant
- UV stabilized
- EU1935/2004 - conform
- EU10/2011 - conform

Colour:

blue FN5884

Range of applications:

- bulk goods handling
- Conveyor industry
- Earth moving conveyors
- Chuts, Hoppers, Silos, buckets etc.

PRODUCT INFORMATION
OKULEN® 2000 - blue - FN5884

Characteristics and standard values

Properties	Method	OKULEN® 2000 - blue - FN5884	
		SI	US
Physical properties			
Molecular-weight	k.a.	7.0 - 9.0 Mio. g/mol.	7.0 - 9.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.940 g/cm ³	> 58.682 lb/ft ³
Notched impact strength	DINENISO 21304-2 (04/2021)	> 120 kJ/m ²	> 57.06 ft-lb/in ²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	80	80
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 17 N/mm ²	> 2465 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 300 %	> 300 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 650 N/mm ²	> 94250 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0,16	~ 0.16
Dynamic Friction	ASTM D 1894 (2014)	~ 0,12	~ 0.12
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	63 - 65 D	63 - 65 D
Ball indentation hardness	DINENISO 2039	~ 36 N/mm ²	~ 5220 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	135 - 137 °C	275 - 278.6 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft ² -°F
Max. operation temperature	Literature	~ 80 °C	~ 176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	> 1.0E14 Ohm*cm	> 1.0E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	> 1.0E13 Ohm	> 1.0E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		EU	EU

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein
Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com