


**PRODUCT INFORMATION**  
**OKULEN® 500 - AB - blue - FN5990**

OKULEN® OK 500 – AB – FN5990 anti-microbial is a HMW-PE Polymer. It has excellent anti-microbial protection. The protection range which has been measured is 99,99 % against bacteria “Staphylococcus aureus ATCC6538P” and “Klebsiella pneumoniae ATCC 4352”. This grade is EU & FDA compliant for food industry.



Properties:

- excellent anti-microbial protection
- water repellent
- FDA - conform
- EU1935/2004 - conform
- EU10/2011 - conform



Colour:

blue - FN5990 / similar RAL 5015

Range of applications:

- Hospital protection boards
- Food industry

<p><b>Ottensteiner Kunststoff GmbH &amp; Co. KG</b> Im Garbrock 39, 48683 Ahaus-Ottenstein Germany</p>	<p>Phone: +49 (0) 2561-9824-0 Internet: <a href="http://www.okulen.com">www.okulen.com</a> e-mail: <a href="mailto:info@okulen.com">info@okulen.com</a></p>
--	---

**PRODUCT INFORMATION**  
**OKULEN® 500 - AB - blue - FN5990**

## Characteristics and standard values

Properties	Method	OKULEN® 500 - AB - blue - FN5990	
		SI	US
<b>Physical properties</b>			
Molecular-weight	k.a.	~ 0.5 Mio. g/mol.	~ 0.5 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.950 g/cm <sup>3</sup>	> 59.306 lb/ft <sup>3</sup>
Notched impact strength	DINENISO 21304-2 (04/2021)	> 15 kJ/m <sup>2</sup>	> 7.1325 ft-lb/in <sup>2</sup>
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	360 - 440	360 - 440
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 26 N/mm <sup>2</sup>	> 3770 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 350 %	> 350 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 1000 N/mm <sup>2</sup>	> 145000 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.15 - 0.20	~ 0.15 - 0.20
Dynamic Friction	ASTM D 1894 (2014)	~ 0.10 - 0.15	~ 0.10 - 0.15
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	65 - 67 D	65 - 67 D
Ball indentation hardness	DINENISO 2039	--- N/mm <sup>2</sup>	--- psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
<b>Thermal properties</b>			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	135 - 137 °C	275 - 278.6 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft <sup>2</sup> -°F
Max. operation temperature	Literature	~ 80 °C	~ 176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
<b>Electrical properties</b>			
Volume resistivity	DINEN 62631-3-1 (01/2017)	> 1E14 Ohm*cm	> 1E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	> 1E13 Ohm	> 1E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
<b>Burning properties</b>			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
<b>Physiological properties</b>			
Food compliant		EU/FDA	EU/FDA

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)